LIFE Series

alphatile & stone

121

1000 designs for Geraldine a


ALEXEY BROD

Available Colors



SMOKE

Available Options



Colored Body Glazed Stoneware

9 9 9 9 9

POLAR 8 x 36 PAN 8X36 LIPO

All items shown in this document are part of Alpha's stocking program. For special orders, please contact your Alpha Tile Sales Representative.

WAPPLETH



A DE LIL



POLAR

alphatile & stone

Colored Body Glazed Stoneware

HAY 8 x 36 PAN 8X36 LIHA







Colored Body Glazed Stoneware

SMOOTH 8 x 36 PAN 8X36 LIST










alphatile & stone a division of olympiatile+stone

Colored Body Glazed Stoneware


SMOKE 8 x 36 PAN 8X36 LISK







alphatile & stone











BOURBON

alphatile & stone = a division of olympiatile+stone





Member **Color Variation V2** V1 **V4** V3 Member of Canada Member of U.S. The Terrazzo, Tile, and Ceramic Tile Marble Institute Green Building Green Building Marble Association of Distributors of of America Council Canada America (CTDA) Council

Packing Details

TILE SIZE

HERRINGBONE 10X24

8" x 36"

PC/BOX

6

6

SF/BOX

11.95

5.54

For information concerning LEED, please contact our Sales Representative

LB/BOX

54.23

27.60


ve

BOX/PAL

48

35

Examples of Recommended Applications



MORE	"MORE" Surface Care Product Guide			
Task	Product Recommendation	Dilution with Water	Frequency	
Grout Sealing	MORE™ Grout, Ceramic & Porcelain Sealer	Ready to use	Commercial: 1-3 Years Residential: 5-8 Years	
Daily Maintenance	MORE [™] Stone and Tile Cleaner	1 : 128 Ratio	Daily	
Deep Cleaning	MORE [™] Alkaline Cleaner	1:4 Ratio	As Needed	
Grout Haze- Cementitious	MORE [™] Acidic Cleaner	1:4 Ratio	As Needed	
Grout Haze - Epoxy / Urethane	MORE [™] Coating Stripper*	Ready to use	As Needed	

* Always test in an inconspicuous area to make sure the product is achieving the desired results and is not damaging the finish of the surface.

alphatile & stone

TECHNICAL FEATURES

Coloured-body glazed stoneware _ According to ANSI A137.1 (Glazed Porcelain Tiles - P1 Class)

	TECHNICAL FEATURES	TEST METHOD	REQUIRED VALUES - ANSI A137.1	LIFE AVERAGE VALUES
	WATER ABSORPTION	ASTM C373	≤ 0.5%	CONFORMS
	BREAKING STRENGTH	ASTM C648	≥ 250 lbf	425 lbf 10 mm
PEI	SURFACE ABRASION RESISTANCE	ASTM C1027	AS INDICATED BY MANUFACTURER	PEI 3 SMOOTH - BOURBON - SMOKE PEI 4 POLAR - HAY
	LINEAR THERMAL EXPANSION	ASTM C372	NO PROVISION	α ≤ 8 x 10 ⁻⁶ °C ⁻¹ α ≤ 4.4 x 10 ⁻⁶ °F ⁻¹
*	STAIN RESISTANCE	ASTM C1378	AS INDICATED BY MANUFACTURER	A RESISTANT
	CHEMICAL RESISTANCE	ASTM C650	AS INDICATED BY MANUFACTURER	A RESISTANT (*)
*	FROST RESISTANCE	ASTM C1026	AS INDICATED BY MANUFACTURER	RESISTANT
	BOND STRENGHT	ASTM C482	≥ 50 PSI	CONFORMS
	SLIP RESISTANCE	ANSI A326.3	DCOF ≥ 0.42	≥ 0.42
	SHADE VARIATION	ANSI A137.1	AS INDICATED BY MANUFACTURER	V2 Slight variation
٢	FLAME SPREAD	ASTM E84	-	Class A
	THERMAL CONDUCTIVITY	EN 12524	-	λ = 1,3 W/m °K / 0.7 BTU/ft h °F
	RECOMMENDED MINIMUM JOINT	NOT RECT	-	3-4 mm APPROX (Indoor)
	THICKNESS	ALL SIZES	-	10 mm

(*) Excluding hydrofluoric acid and its derivatives

Technical data is supplied by the manufacturer and is subject to change at any time. Olympia or Alpha does not provide warranties as to the specifications of any product.

alphatile & stone

Tampa

2443 East Meadow Blvd. Tampa, FL 33619 (813) 620-9000 (800) 785-9000

Fort Myers

10898-A Metro Parkway Ft. Myers, FL 33966 (239) 275-8288 (800) 785-8288

Sarasota

1808 Whitfield Ave. Sarasota, FL 34243 (941) 727-7433 (800) 785-3484

Orlando

2603 Ace Road Orlando, FL 32804 (407) 293-3993 (800) 785-3993



www.alphatile.com